

BENTOSWELL-SALT

Description

Hydrophilic, swellable waterstop made of high quality sodium bentonite and butyl rubber for the preventive sealing of construction joints and as a system component for bentonite mats. BENTOSWELL-SALT retains its shape after 3 wet and dry cycles (MFPA certified). However, at some point there will be some wash-out. The advantage of this phenomenon is that concrete voids/cracks are filled. BENTOSWELL-SALT has a good resistance to a wide range of chemicals.

Application

BENTOSWELL-SALT can be applied both vertically and horizontally, but under no circumstances should it be used in expansion joints. Place the BENTOSWELL-SALT on a smooth and dust-free surface (concrete). To ensure a continuous section of the sealing bar, an overlap of 5 to 10 cm is applied and the ends of the bars are firmly pressed together. A minimum concrete cover of 6 cm on each side is required. Do not install BENTOSWELL-SALT during heavy rainfall as this may cause swelling before the concrete has been poured onto the sealing bar. Avoid any contact with water before pouring concrete. BENTOSWELL-SALT is installed between the inside and outside reinforcement. BENTOSWELL-SALT can be fixed by using bentonite waterstop fixing glue or by gun nailing with wire mesh. For vertical applications, the use of a wire mesh is recommended. The mesh and bar are then fixed by gun nailing. BENTOSWELL-SALT bars that are damaged, already swollen, or whose geometry has changed may not be installed. The usability of the product in the respective installation situation must be checked by the user!




1. Ensure full contact with the joint. If required use fixing glue.
2. Unroll the BENTOSWELL-SALT between the first phase starter bars with a minimum concrete cover of 6 cm.
3. Install wire mesh over the BENTOSWELL-SALT. In order to ensure good contact with the construction joint surface, shotfire the wire mesh every 25 cm, using nails with washers.

Material

- Sodium bentonite
- Butyl rubber
- Free from PVC, CFC and HFC
- Without substances of very high concern according to ECHA candidate list (REACH Regulation)

Packaging

- Free of halogen-containing compounds, azo dyes, flame retardants



BENTOSWELL-SALT

Item no.	Dimension mm	Length m	Rolls/ Box	m/ Box	m/ Pallet
BSS192405/06	19 x 24	5,00	6	30,00	1.620,00
BSS201010/06	20 x 10	10,00	5	50,00	3.150,00
BSS202505/06	20 x 25	5,00	6	30,00	1.620,00



Technical data:

Volume expansion in rain water: 350 %

Volume expansion in concrete water: 200 %

Volume expansion in 3 % salt water: 150 %

Colour: Red

Density: 1.45 g/m³

Swelling pressure when encapsulated: Approx. 32 kN/m (MFPA Leipzig)

Resistance to hydrostatic pressure: Tested up to 5 bar (MFPA Leipzig)

Bending radius on the corners: 50 mm

Application Temperature : 0 / +50 °C

Service Temperature: -50 / +70 °C

Tolerance range (dimensions) +/-1.0 mm

These data are not suitable for the issue of specifications. Please contact our Sales Office before issuing specifications.

Weather resistance: Excellent UV and ozone resistance. Avoid long term exposure to direct sunlight.

Chemical resistance: Good general chemical resistance to acids, alkalis and most aqueous solutions but caution is advised with aromatic oils and fuels, vegetable oils and strong aromatic solvents. Contact our Sales Office for detailed specific information.

Chemicals (concentration 1-10%) - Resistance

Inorganic acids - No effect

Inorganic bases - No effect

Organic acids/bases - No effect

Alcohols - No effect

Aldehydes - No effect

Amines - No effect

Ester - No effect

Ether - No effect

Detergents and other cleaning agents - No effect

Chlorine water - No effect

Aromatic hydrocarbons:

Benzene - Moderate effect

Nitrobenzene - Moderate effect

Toluene - Moderate effect

Xylene - Moderate effect

100/150 solvents - Moderate effect

Aliphates hydrocarbons (oils and fuels) - Moderate effect

Halogenated hydrocarbons - Moderate effect

Carbon disulphides - Moderate effect



For further documents
scan or click here!



BENTOSWELL-SALT

Biological fats, oils and sugars - Moderate effect

No effect: Performance will not be affected under most service conditions.

Moderate effect: Performance may be affected, especially with long-term exposure.

For information on chemical resistance to chemicals in concentrations above 10%, please contact our Sales Office.

Note: Protect from direct sunlight and moisture during storage.

